

To:

**James Abramenko**  
 Sherlock Environmental Services  
 228A 12C Street North  
 Lethbridge, Alberta  
 T1H 2M7

**EMC LAB REPORT NUMBER:** A37798

**Job/Project Name:** U of L, Level 4C (Jason)

**Analysis Method:** Polarized Light Microscopy – EPA 600

**Date Received:** Mar 8/18

**Date Analyzed:** Mar 8/18

**Analyst:** Chengming Li, *Analyst*

**Reviewed By:** Fajun Chen, Ph.D., *Laboratory Director*

**Job No:** SES 18488

**Number of Samples:** 1

**Date Reported:** Mar 8/18



Client's Sample ID	Lab Sample No.	Description/Location	Sample Appearance	SAMPLE COMPONENTS (%)			
				Asbestos Fibres		Non-asbestos Fibres	Non-fibrous Material
18488-76	A37798-1	U hall Level C4 laundry Rm	Grey, cementitious material with fibres	Chrysotile	10	20	70

**Note:**

1. Bulk samples are analyzed using Polarized Light Microscopy (PLM) and dispersion staining techniques. The analytical procedures are in accordance with EPA 600/R-93/116 method.
2. The results are only related to the samples analyzed. **ND** = None Detected (no asbestos fibres were observed), **NA** = Not Analyzed (analysis stopped due to a previous positive result).
3. This report may not be reproduced, except in full without the written approval of EMC Scientific Inc. This report may not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government.
4. The Alberta Regulatory Threshold for asbestos is 1%. The limit of quantification (LOQ) is 1%.